

3M™ Safety & Security Film Safety S80

Description

3M™ Safety Film Safety S80 was designed for usage on the interior surface of windows. The film is visco elastic and obsolescence resistant. High resistance of the film to stretch and crack extension increases the resistance of glass to pressure, push and impacts. Even distribution of the sun's rays effectively reduces the effect of dazzle. Besides, the film greatly significantly reduces the amount of UVA rays which are the main reason of discolouration.

3M™ Safety Films provide an effective protection from injuries or damage to items caused the fragments of broken glass. In case of glass breakage the fragments are hold due to the system of the adhesive.

Features (on 6 mm clear glass)

Total solar energy reduction:	21 %
G-value:	0.79
Reduction of Glare:	2 %
Reduction of UV rays:	98 %

Structure of the film

Thickness:	0,2 mm / 200 µ
Colour:	Clear
Material of the film:	Polyester
Adhesive:	Special Acrylic
Top coating:	Scratch resistant hard coat

Installation

3M Window films are installed using water and a soap solution. Full adhesion is reached after approximately 20 days at 18°C (in dry conditions).

Cleaning

3M Window films may be cleaned 30 days after installation using ordinary window cleaning agents and avoiding the use of abrasive particles. Do not use rough sponges, cloths or brushes. Synthetic sponges, soft wipes or rubber squeegee cleaners are recommended. Do not clean 3M films dry.

Glass type	Film Type	SC	VLR %	VLT %	Emissivity	u-value	g-value	TSER
Single Pane								
Clear	No Film	0.94	8 %	88 %	0.84	1.06	0.82	18 %
	Safety S80	0.91	9 %	87 %	0.89	1.04	0.79	21 %
Tinted	No Film	0.69	5 %	50 %	0.84	1.06	0.60	40 %
	Safety S80	0.72	6 %	52 %	0.89	1.04	0.63	37 %
Double Pane								
Clear	No Film	0.81	14 %	78 %	0.84	0.50	0.70	30 %
	Safety S80	0.80	15 %	77 %	0.89	0.48	0.70	30 %
Tinted	No Film	0.55	8 %	45 %	0.84	0.50	0.48	52 %
	Safety S80	0.58	9 %	46 %	0.89	0.48	0.50	50 %

General notes:

All **3M Safety films** have been tested to EN12600 and/or EN356 as appropriate. For detailed information and relevant certification for any specific project, please contact your local 3M specialist.

All technical data is based on a combination of relevant European test methods and/or US test methods. Before using this product the customer / applicator must ensure the product is suitable to be used for the intended purpose. If there is any uncertainty, please check with your local 3M Window Film specialist. All issues regarding warranty and liability for the product and the effect of its use are governed in accordance with the provisions of the appropriate contract of sale unless local laws dictate otherwise.



Renewable energy Division
Window Films
www.3M.com/windowfilms

Your local Window Film Dealer:

Guardian Glazing Film Ltd

Guardian House
Drayton Road
Shirley
Solihull
B90 4NG

Telephone : 0121 693 4747



3M™ Safety & Security Film

Safety S80

- **Increases protection from flying or broken glass.**
- **Deters smash and grab burglaries.**
- **Reduces fading from UV light.**
- **Helps preserve the appearance of furniture and fabrics.**
- **Has an abrasion resistant surface to maintain a good appearance for longer.**
- **Easy to remove without adhesive residues.**